


Material Data - Magnetic Properties



Deep Pot with Internal thread Ferrite holding magnet

Max. working temperature 110°C

Operating temperature depends on the magnet dimension and the specific application.

The pull force given refers to hoisting capacity measured in optimal conditions, by using as a backing plate a sheet made of low-carbon steel, 10 [mm] thick, of smooth surface and with the force acting perpendicularly, in room temperature.

Part No.	ØA	M	B	Grade	Holding Force (Kg)
HM 25 x 7 / M4	25	4	7	C8	2,5
HM 32 x 7 / M4	32	4	7	C8	6
HM 40 x 8 / M4	40	4	8	C8	7
HM 50 x 10 / M6	50	6	10	C8	12,5
HM 63 x 14 / M8	63	8	14	C8	25
HM 80 x 18 / M10	80	10	18	C8	45

(Dimension in mm)

All values indicated were determined on standard samples. Depending on the shape and dimensions there could occur deviations.



The product conforms to the European RoHS Community legislation (2002/95/EG - RoHS - Restriction of Hazardous Substances) relating to the use and the employment of certain hazardous substances in electrical and electronic devices. No subject to registration under the REACH Regulation.



Read the Safety Warnings before handling the magnets.

Best Magnet is a Vega Technik GmbH product division.

For more information please contact **Vega Technik GMBH** Ackerweg 9 - 9500 Villach Austria tel. +43(0)424221174 info@vegatechnik.com - www.vegatechnik.com